


Catalog # 26-1600 Ethylferrocene, 98%



Thermal Behavior:

- Boiling point: 108-109°C/5.5 Torr

Technical Notes:

1. Precursor for iron oxide film deposition.

Target Deposit	Deposition Technique	Delivery Temperature	Pressure	Co-reactants	Deposition Temperature	Ref.
FeO _x	PA-ALD	100-110°C	1 Torr	^P LO ₂	150-250°C	1

References:

1. [Surf. Coat. Technol. 2021, 421, 127390.](#)