

## CdSe

Strem offers the following Quantum Dots


### Core: CdSe



The CdSe core is highly uniform with a narrow particle size distribution ( $\pm 10\%$ ) and proves to be a very good absorber material. They are surrounded by organic ligands (oleylamine, phosphonic compounds). This structure ideally stabilizes the quantum dot properties from the core.

#### Product characteristics:

- Size dependant absorption and emission properties
- Long-term stability
- Scalability (produced via continuous flow)
- High batch-to-batch reproducibility (TEM available for each lot)
- Emission range 525-625nm
- Homogeneous dispersions in different non-polar solvents possible
- Use as absorber material or coating



Structure	Ligand Capping Agent	Stability of Dispersions	Quantum Yield	Emission Range
CdSe core	Oleylamine	6 months	low	525-625nm

Visit [www.strem.com](http://www.strem.com) for new product information and searchable catalog.

**Strem Chemicals, Inc.**  
7 Mulliken Way  
Newburyport, MA 01950-4098  
U.S.A.  
Tel.: (978) 499-1600  
Fax: (978) 465-3104  
Email: [info@strem.com](mailto:info@strem.com)

**Strem Chemicals, Inc.**  
15, rue de l'Atome  
Zone Industrielle  
67800 BISCHHEIM France  
Tel.: (33) 03 88 62 52 60  
Fax: (33) 03 88 62 26 81  
Email: [info.europe@strem.com](mailto:info.europe@strem.com)

**Strem Chemicals, Inc.**  
Postfach 1215  
77672 KEHL  
Germany  
Telefon: 0 78 51/ 7 58 79  
Email: [info.europe@strem.com](mailto:info.europe@strem.com)

**Strem Chemicals UK Ltd.**  
An Independent Distributor of  
Strem Chemicals products  
Newton Hall, Town St.  
Newton  
Cambridge CB22 7ZE, UK  
Tel.: 0845 643 7263  
Fax: 0845 643 7362  
Email: [enquiries@strem.co.uk](mailto:enquiries@strem.co.uk)





Peak Emission	Particle Size (diameter)	Strem Catalog No. (in hexane)+	Quantum Yield
<b>CdSe core</b>			
525nm	2.8nm	48-1011	low
550nm	3.5nm	48-1017	low
575nm	3.9nm	48-1023	low
600nm	4.7nm	48-1030	low
625nm	5.3nm	48-1035	low
Kit: 525-625nm		96-0800	low

Kit contains 5ml of each of the above 5 products. Ligand capping agent oleylamine. Stable in dispersions 6 months.

† Available at nanoparticle concentration of 50µmol per liter.

Store cold in dark under inert atmosphere. Do not freeze.

### Typical spectra for CdSe core quantum dots.



**Visit [www.strem.com](http://www.strem.com) for new product information and searchable catalog.**

**Strem Chemicals, Inc.**  
 7 Mulliken Way  
 Newburyport, MA 01950-4098  
 U.S.A.  
 Tel.: (978) 499-1600  
 Fax: (978) 465-3104  
 Email: [info@strem.com](mailto:info@strem.com)

**Strem Chemicals, Inc.**  
 15, rue de l'Atome  
 Zone Industrielle  
 67800 BISCHEIM France  
 Tel.: (33) 03 88 62 52 60  
 Fax: (33) 03 88 62 26 81  
 Email: [info.europe@strem.com](mailto:info.europe@strem.com)

**Strem Chemicals, Inc.**  
 Postfach 1215  
 77672 KEHL  
 Germany  
 Telefon: 0 78 51/ 7 58 79  
 Email: [info.europe@strem.com](mailto:info.europe@strem.com)

**Strem Chemicals UK Ltd.**  
 An Independent Distributor of  
 Strem Chemicals products  
 Newton Hall, Town St.  
 Newton  
 Cambridge CB22 7ZE, UK  
 Tel.: 0845 643 7263  
 Fax: 0845 643 7362  
 Email: [enquiries@strem.co.uk](mailto:enquiries@strem.co.uk)

