


Catalog # 78-1358 (Trimethyl)pentamethylcyclopentadienylplatinum(IV), 99%

**Thermal behaviour**

- Melting point 90 °C [1]
- Sublimation (for purification) at 40 °C and 0.13 mbar [1]

Technical Notes

Mixed alkyl-cyclopentadienyl platinum compound with beneficial precursor properties for the deposition of **platinum** thin films by CVD and ALD.

References:

1. Inorg. Chem., **1989**, 28, 872.