


96-1530 Gold Nanorods Kit (Axial Diameter-25nm, wavelength 550-700nm)


Contains 25ml of each of the following:

79-6000	Gold Nanorods (Axial Diameter-25nm) (Wavelength 550nm)
79-6005	Gold Nanorods (Axial Diameter-25nm) (Wavelength 600nm)
79-6010	Gold Nanorods (Axial Diameter-25nm) (Wavelength 650nm)
79-6015	Gold Nanorods (Axial Diameter-25nm) (Wavelength 700nm)



Additional sizes can be supplied. Please inquire.

Gold nanorods are shipped in 18MΩ DI water with < 0.1% ascorbic acid and < 0.1% CTAB surfactant capping agent.



Representative TEMS

Storage Instructions

Store at 4°C. Do not freeze. CTAB, may cause a cloudy appearance at low temperatures. Before use, warm to room temperature to resuspend excess CTAB. Particularly for the larger nanorods, make sure to homogenize bottles after long storage periods to resuspend any sedimentation.

Shelf life 6 months.

Typical Characteristics (Specifications)

Axial diameter = 25 nm
Axial peak SSRP = 530 nm

Part #	Longitudinal Size (nm)	Peak LSPR Wavelength (nm)	Wt. Conc (ug/ml)	LSPR Molar Ext. (M-1cm-1)	SSPR Molar Ext. (M-1cm-1)
79-6000	34	550	170.5	9.15E+08	5.72E+08
79-6005	47	600	235.1	1.03E+09	5.72E+08
79-6010	60	650	149.8	2.29E+09	1.14E+09
79-6015	73	700	91.1	4.58E+09	2.29E+09

SPR = Surface plasmon resonance
LSPR = Longitudinal SPR peak
SSPR = Axial SPR peak
Shape monodispersity (% rods) > 95%
Size variation +/-10% (both dimensions)
Aspect ratio variation = Peak LSPR accuracy/96
All specs typical. May vary batch to batch.

Visit www.strem.com for new product information and searchable catalog.

Strem Chemicals, Inc.
7 Mulliken Way
Newburyport, MA 01950-4098
U.S.A.
Tel.: (978) 499-1600
Fax: (978) 465-3104
Email: info@strem.com

Strem Chemicals, Inc.
15, rue de l'Atome
Zone Industrielle
67800 BIRSCHHEIM France
Tel.: (33) 03 88 62 52 60
Fax: (33) 03 88 62 26 81
Email: info.europe@strem.com


Strem Chemicals, Inc.
Postfach 1215
77672 KEHL
Germany
Telefon: 0 78 51/ 7 58 79
Email: info.europe@strem.com

Strem Chemicals UK, Ltd.
41 Hills Road
Cambridge
England CB2 1NT
Tel.: 0845 643 7263
Fax: 0845 643 7362
Email: enquiries@strem.co.uk

96-1535 Gold Nanorods Kit (Axial Diameter - 10nm, wavelength 700-808nm)


Contains 25ml of each of the following:

79-6020	Gold Nanorods (Axial Diameter - 10nm) (Wavelength 700nm)
79-6025	Gold Nanorods (Axial Diameter - 10nm) (Wavelength 750nm)
79-6030	Gold Nanorods (Axial Diameter - 10nm) (Wavelength 780nm)
79-6035	Gold Nanorods (Axial Diameter - 10nm) (Wavelength 808nm)



Additional sizes can be supplied. Please inquire.

Gold nanorods are shipped in 18MΩ DI water with < 0.1% ascorbic acid and < 0.1% CTAB surfactant capping agent.



Representative TEMS

Storage Instructions

Store at 4°C. Do not freeze. CTAB, may cause a cloudy appearance at low temperatures. Before use, warm to room temperature to resuspend excess CTAB. Particularly for the larger nanorods, make sure to homogenize bottles after long storage periods to resuspend any sedimentation.

Shelf life 6 months.

Typical Characteristics (Specifications)

Axial diameter = 10 nm
Axial peak SSRP = 512 nm

Part #	Longitudinal Size (nm)	Peak LSPR Wavelength (nm)	Wt. Conc (ug/ml)	LSPR Molar Ext. (M-1cm-1)	SSRP Molar Ext. (M-1cm-1)
79-6020	29	700	29.7	8.99E+08	2.25E+08
79-6025	35	750	33.4	9.40E+08	2.35E+08
79-6030	38	780	34.9	9.81E+08	2.45E+08
79-6035	41	808	36.1	1.02E+09	2.55E+08

SPR = Surface plasmon resonance

LSPR = Longitudinal SPR peak

SSRP = Axial SPR peak

Shape monodispersity (% rods) > 95%

Size variation +/-10% (both dimensions)

Aspect ratio variation = Peak LSPR accuracy/96

All specs typical. May vary batch to batch.

Visit www.strem.com for new product information and searchable catalog.

Strem Chemicals, Inc.
7 Mulliken Way
Newburyport, MA 01950-4098
U.S.A.
Tel.: (978) 499-1600
Fax: (978) 465-3104
Email: info@strem.com

Strem Chemicals, Inc.
15, rue de l'Atome
Zone Industrielle
67800 BISCHHEIM France
Tel.: (33) 03 88 62 52 60
Fax: (33) 03 88 62 26 81
Email: info.europe@strem.com

Strem Chemicals, Inc.
Postfach 1215
77672 KEHL
Germany
Telefon: 0 78 51/ 7 58 79
Email: info.europe@strem.com

Strem Chemicals UK, Ltd.
41 Hills Road
Cambridge
England CB2 1NT
Tel.: 0845 643 7263
Fax: 0845 643 7263
Email: enquiries@strem.co.uk



Gold nanorods (GNRs) exhibit transverse and longitudinal surface plasmon resonances (SPR) that correspond to electron oscillations perpendicular and parallel to the rod length direction, respectively. Their longitudinal surface plasmon wavelengths (LSPWs) are tunable from the visible to infrared regions. Their absorption cross sections are at least five orders larger than those of conventional dyes, and the light scattering by Au nanorods is several orders larger than the light emission from strongly fluorescent dyes.¹⁻³ The tunability in the LSPW, together with strongly enhanced scattering and absorption at the LSPW, makes GNRs useful for the formation of many functional composite materials, for example, with hydrogel,^{4,5} polymers,^{6,7} silica,⁸ and bacteria.⁹ GNRs also have an axial surface plasmon resonance (SSPR), though one-third that of the LSPR, is still many orders of magnitude greater than quantum dots and nanoshells. GNRs also offer advantages of good biocompatibility, facile preparation, and conjugation with a variety of biomolecular ligands, antibodies, and other targeting moieties.¹⁰ They have therefore found wide applications in biochemical sensing,¹¹ biological imaging, medical diagnostics, and therapeutics.¹²⁻¹⁶ Further, GNRs have found application in materials and optics, including polarizers, filters, and to improve the storage density in compact disks.

The effectiveness of GNRs as scattering-based biomedical imaging contrast agents and as photothermal therapeutic agents is strongly dependent on their scattering and absorption cross sections. In general, high scattering cross sections are favorable for cellular and biological imaging based on darkfield microscopy, while large absorption cross sections with small scattering losses allow for photothermal therapy with a minimal laser dosage. In addition, the LSPWs of GNRs are strongly desired to be in the spectral range of 650–900 nm). Light irradiation in this region can penetrate deeper in tissues and cause less photodamage than UV–visible irradiation.¹⁷ Therefore, the ability to tailor both scattering and absorption of GNRs with different LSPWs is of ultimate importance for practical *in vivo* biomedical imaging and therapeutic applications.¹⁸⁻²⁰

References:

1. Lee, K.-S.; El-Sayed, M. A. Dependence of the Enhanced Optical Scattering Efficiency Relative to That of Absorption for Gold Metal Nanorods on Aspect Ratio, Size, End-Cap Shape, and Medium Refractive Index. *J. Phys. Chem. B* **2005**, *109*, 20331–20338.
2. Jain, P. K.; Lee, K. S.; El-Sayed, I. H.; El-Sayed, M. A. Calculated Absorption and Scattering Properties of Gold Nanoparticles of Different Size, Shape, and Composition: Applications in Biological Imaging and Biomedicine. *J. Phys. Chem. B* **2006**, *110*, 7238–7248.
3. Chen, W. R.; Adams, R. L.; Carubelli, R.; Nordquist, R. E. Laser-Photosensitizer Assisted Immunotherapy: A Novel Modality for Cancer Treatment. *Cancer Lett.* **1997**, *115*, 25–30.
4. Gorelikov, I.; Field, L. M.; Kumacheva, E. Hybrid Microgels Photoresponsive in the Near-Infrared Spectral Range. *J. Am. Chem. Soc.* **2004**, *126*, 15938–15939.
5. Karg, M.; Pastoriza-Santos, I.; Pérez-Juste, J.; Hellweg, T.; Liz-Marzán, L. M. Nanorod-Coated PNIPAM Microgels: Thermoresponsive Optical Properties. *Small* **2007**, *3*, 1222–1229.
6. Pérez-Juste, J.; Rodríguez-González, B.; Mulvaney, P.; Liz-Marzán, L. M. Optical Control and Patterning of Gold-Nanorod-Poly(vinyl alcohol) Nanocomposite Films. *Adv. Funct. Mater.* **2005**, *15*, 1065–1071.
7. Murphy, C. J.; Orendorff, C. J. Alignment of Gold Nanorods in Polymer Composites and on Polymer Surfaces. *Adv. Mater.* **2005**, *17*, 2173–2177.
8. Chon, J. W. M.; Bullen, C.; Zijlstra, P.; Gu, M. Spectral Encoding on Gold Nanorods Doped in a Silica Sol-Gel Matrix and Its Application to High-Density Optical Data Storage. *Adv. Funct. Mater.* **2007**, *17*, 875–880.
9. Berry, V.; Gole, A.; Kundu, S.; Murphy, C. J.; Saraf, R. F. Deposition of CTAB-Terminated Nanorods on Bacteria to Form Highly Conducting Hybrid Systems. *J. Am. Chem. Soc.* **2005**, *127*, 17600–17601.
10. Katz, E.; Willner, I. Integrated Nanoparticle-Biomolecule Hybrid Systems: Synthesis, Properties, and Applications. *Angew. Chem., Int. Ed.* **2004**, *43*, 6042–6108.
11. Sudeep, P. K.; Joseph, S. T. S.; Thomas, K. G. Selective Detection of Cysteine and Glutathione Using Gold Nanorods. *J. Am. Chem. Soc.* **2005**, *127*, 6516–6517.
12. Wang, H. F.; Huff, T. B.; Zweifel, D. A.; He, W.; Low, P. S.; Wei, A.; Cheng, J.-X. *In Vitro* and *In Vivo* Two-Photon Luminescence Imaging of Single Gold Nanorods. *Proc. Natl. Acad. Sci. U.S.A.* **2005**, *102*, 15752–15756.
13. Durr, N. J.; Larson, T.; Smith, D. K.; Korgel, B. A.; Sokolov, K.; Ben-Yakar, A. Two-Photon Luminescence Imaging of Cancer Cells Using Molecularly Targeted Gold Nanorods. *Nano Lett.* **2007**, *7*, 941–945.
14. Huang, X. H.; El-Sayed, I. H.; Qian, W.; El-Sayed, M. A. Cancer Cells Assemble and Align Gold Nanorods Conjugated to Antibodies to Produce Highly Enhanced, Sharp, and Polarized Surface Raman Spectra: A Potential Cancer Diagnostic Marker. *Nano Lett.* **2007**, *7*, 1591–1597.
15. Huang, X. H.; El-Sayed, I. H.; Qian, W.; El-Sayed, M. A. Cancer Cell Imaging and Photothermal Therapy in the Near-Infrared Region by Using Gold Nanorods. *J. Am. Chem. Soc.* **2006**, *128*, 2115–2120.
16. Chen, C.-C.; Lin, Y.-P.; Wang, C.-W.; Tzeng, H.-C.; Wu, C.-H.; Chen, Y.-C.; Chen, C.-P.; Chen, L.-C.; Wu, Y.-C. DNAGold Nanorod Conjugates for Remote Control of Localized Gene Expression by Near Infrared Irradiation. *J. Am. Chem. Soc.* **2006**, *128*, 3709–3715.
17. Weissleder, R. A Clearer Vision for *In Vivo* Imaging. *Nat. Biotechnol.* **2001**, *19*, 316–317.
18. Hirsch, L. R.; Stafford, R. J.; Bankson, J. A.; Sershen, S. R.; Rivera, B.; Price, R. E.; Hazle, J. D.; Halas, N. J.; West, J. L. Nanoshell-Mediated Near-Infrared Thermal Therapy of Tumors under Magnetic Resonance Guidance. *Proc. Natl. Acad. Sci. U.S.A.* **2003**, *100*, 13549–13554.
19. Loo, C.; Lowery, A.; Halas, N.; West, J.; Drezek, R. Immunotargeted Nanoshells for Integrated Cancer Imaging and Therapy. *Nano Lett.* **2005**, *5*, 709–711.
20. Chen, J. Y.; Saeki, F.; Wiley, B. J.; Cang, H.; Cobb, M. J.; Li, Z.-Y.; Au, L.; Zhang, H.; Kimmey, M. B.; Li, X. D.; Xia, Y. N. Gold Nanocages: Bioconjugation and Their Potential Use as Optical Imaging Contrast Agents. *Nano Lett.* **2005**, *5*, 473–477.
21. Weihai Ni, Xiaoshan Kou, Zhi Yang, and Jianfang Wang, Tailoring Longitudinal Surface Plasmon Wavelengths, Scattering and Absorption Cross Sections of Gold Nanorods, *ACS Nano*, Vol. 2 No. 4, 677–686, **2008**.

Visit www.strem.com for more information.