

Catalog #13-1402 Aluminum oxide nanopowder (high surface area)

Specific Surface Area (BET):	≥ 550 m ² /g	True Density:	2.9 g/cc
Crystallite Size:	Amorphous	Mean Aggregate Size:	5 μm
Average Pore Diameter:	110Å	Loss on Ignition:	≤ 13%
Total Pore Volume:	≥1.5 cc/g	Moisture Content:	≤ 12%
Bulk Density:	0.20 g/cc	Al Content (Based on Metal):	>99.2%