




40-1125 • UiO-66 MMM is a MOF that is incorporated into polymer mixed-matrix membrane (MMM) with ~60 wt% UiO-66 MOF loading. MMM is prepared from polyvinylidene difluoride (PVDF), which acts as an effective binder for MOF, while still allowing the pores to be permeable and accessible to adsorbates ^[1-2].

The MOF/PVDF films form homogeneous layered structures after drying, giving durable, large-area, freestanding MMMs with good mechanical stability and flexibility. Characterization of the films showed that the MOFs are highly crystalline and remain porous within the MMM (**BET surface area: 650-700 m²/g**)

UiO-66 MMM allows further chemical modification through postsynthetic modification and postsynthetic exchange processes.



SEM images of UiO-66 MMM (~60 wt%) with cross-section and plane-view

UiO-66 MMM is resilient to mechanical stress and can be easily handled in ambient conditions using nitrile gloves (recommended). The long-term storage (>1 week) should be performed under moisture-free conditions. The **UiO-66 MMM** is light- and dry-air-stable.

References:

1. *Angew. Chem. Int. Ed.* **2015**, *54*, 9029
2. *Chem. Sci.*, **2016**, *7*, 2711

Visit www.strem.com for new product information and a searchable catalog.

Strem Chemicals, Inc.
7 Mulliken Way
Newburyport, MA 01950
U.S.A
Tel: 978.499.1600
Fax: 978.465.3104
Email: info@strem.com

Strem Chemicals, Inc.
15 rue de l'Atome
Zone Industrielle
67800 BISCHHEIM France
Tel: (33) 03 88 62 52 60
Fax: (33) 03 88 62 26 81
Email: info.europe@strem.com

Strem Chemicals, Inc.
Postfach 1215
77672 KEHL
Germany
Tel: 0 78 51/ 7 58 79
Email: info.europe@strem.com

Strem Chemicals UK Ltd.
An Independent Distributor of Strem Chemicals Products
Newton Hall, Town Street
Newton, Cambridge
England CB22 7ZE
Tel: 0845 643 7263
Fax: 0845 643 7362
Email: enquiries@strem.co.uk