

Catalog #22-1400 Titanium (IV) oxide nanopowder Anatase

Specific Surface Area (BET):	≥ 500 m <sup>2</sup> /g	True Density:	3.7 g/cc
Crystallite Size:	Amorphous	Mean Aggregate Size:	5 μm
Average Pore Diameter:	32Å	Loss on Ignition:	≤ 12%
Total Pore Volume:	≥0.4 cc/g	Moisture Content:	≤ 4%
Bulk Density:	0.6 g/cc	Ti Content (Based on Metal):	>99.999%